



P  
T

155

**Ms**

**Mesh Sport**

100 % Polyester

## MESH SPORT

Article No. 06109-2200

“The fabric is knitted material made from a combination of mesh and piqué construction. The face side has a honeycomb surface.”

The thinner, airier honeycombs lie alternately mesh-like next to thicker honeycombs. This type ensures optimal air transport during physical activity. The synthetic material ensures extremely short drying times. “Mesh Sport” is a very stretchy product and adapts to every body movement.

### Facts


Composition	100 % Polyester
Construction	Knitted
Width <sup>1</sup> brutto	160 cm
Weight	155 g/m <sup>2</sup>
Shrinkage	Length < 3.5 % Width < 3.5 %
Selvedge	glued selvedge, 1,5 cm
Calender	195 °C, 52 Seconds

<sup>1</sup> Due to the stretchable construction of knitted fabrics, deviations of +/- 2cm may occur.

### Applications

Sport Shirts, Tops

### Care label



Please wash separately!

### Print technology & Features



\*Discover the tips and tricks for a perfect printing textile: download the guide from the link below or scanning the QR code.



Printing on Textile Guide

[https://bergertextiles.com/wp-content/uploads/2022/11/Printing-on-textile-DE-EN\\_21x11cm.pdf](https://bergertextiles.com/wp-content/uploads/2022/11/Printing-on-textile-DE-EN_21x11cm.pdf)

**\*Important: Always perform print test!** Many parameters influence the print result: printer, type of ink, textile, room climate, intended use and much more. An ideal print result can only be achieved in combination. That is why we at **bergertextiles** recommend only the printing processes for a product that will achieve the best results. The recommendations are the result of intensive print tests and must meet the highest demands in terms of print quality. Often it is also possible to print the textiles with other printing processes. In these cases, the individual requirements and technical possibilities are very important. All technical information was determined according to the current state of measurement technology and reflects the values of the test sample. Despite the highest quality standards, there may be deviations in production technology - all information is not legally binding and without guarantee.